

HETEROGENEOUS SHEET

Timberline® (Asia)

Product Information

Construction - Solid Heterogeneous

Product Line – Timberline (Asia)

Factory Finish - TrueShield for HET

Installation - Full Spread Adhesive

Technical Data	Test Standard	Test Requirement / Method	Rating / results
Sheet width	ISO 24341	-	2 m
Sheet length	ISO 24341	-	15-20 m
Overall Thickness	ISO 24346	-	2.0 mm
Wear Layer Thickness	ISO 24340	-	0.55 mm
Fire Test			
Fire resistant	EN 13501	-	Bfl-s1
Smoke toxicity test	EN 45545-2	-	Passed
Environmental and Classifications			
Commercial	ISO 10874	-	Class 33
Cleanliness / Cleanroom	ISO 14644	-	ISO Class 4
TVOC	ISO 16000-9	-	Not detected
Phthalates	EN 14372	-	Not detected
Heavy metals	EN 71-3	-	Not detected
Mould Resistance	ASTM G 21	-	No growth
Resistance to bacteria	ISO 846 C	-	No growth
Antimicrobial Activity	ISO 22196	-	>99.9%
Performance			
Slip Resistance	DIN 51130	-	R10
Flexibility	ISO 24344 A	20mm mandrel no cracking	Passed
Wear Resistance	EN 660-2	Rating (Highest) T, P, M, F (Lowest)	Group T
Seam Strength	EN 648	≥ 400 N/ 50mm	Passed
Residual Indentation	ISO 24343-1	≤ 0.10 mm	Passed
Dimensional Stability	ISO 23999	≤ 0.40%	Passed
Colour fastness	ISO 105-B02	≥ Grade 6	Passed
Chemical Staining Resistance	ISO 26987	Duration of Contact 2 hrs (85 items)	Not affected
Castor Chair	ISO 4918	25,000 cycles	Passed
Impact Sound Reduction	ISO 10140-3	-	4dB
Antistatic (Body voltage)	EN 1815 A	≤ 2.0kV	Passed

Limited warranty

10-year Commercial Warranty when installed in strict accordance with the detailed instructions.

Visit www.armstrongflooring.asia

for complete Product, Technical, Adhesives, Installation & Maintenance recommendations.